

Disflamoll® 51092

Phosphorus Flame Retardants

Description

Phosphate ester with good plasticizing efficiency and flame retardant characteristics in many polymers.

Chemical Composition

Butylated triphenyl phosphate

Appearance

Clear, almost colorless liquid.

Solubility

Soluble in many organic solvents like toluene, methanol, acetone, MEK, also compatible with polyether and polyester polyol as well as with all common plasticizers. Insoluble in water.

Typical Properties*

Property	Nominal Value	Unit
Phosphorus content, calculated	8.5	%
Acid value	max. 0.1	mg KOH/g
Water content	max. 0.1	%
Hazen color value	max. 75	#
Refractive index n_D 20 °C	1.554 - 1.558	#
Density at 20 °C	1.17 - 1.19	g/cm ³
Viscosity at 20 °C	60 - 110	mPa·s

*The analytical data are guide values.



Disflamoll® 51092

Phosphorus Flame Retardants

Application

Disflamoll® 51092 is mostly used as a plasticizing flame retardant in flexible PVC. It can also be used as a flame retardant for polyurethanes (TPU), elastomers and thermosets. Disflamoll® 51092 is not compatible with completely nonpolar polymers such as polyethylene or polypropylene.

Packaging

Road tankers / containers.

Storage conditions

If stored correctly, the product has a minimum shelf life of two years. At sub-zero temperatures triphenyl phosphate may crystallize and form a precipitate. This can be dissolved again when heated up without any adverse effect on quality.

Handling

Consult the safety data sheet for relevant safety data & references as well as possibly necessary warning labels.

® = registered trade mark

This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2021 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America
+1.833.LANXESS
customer.care@lanxess.com

Europe, Middle East & Africa
+44.161.875.3800
emea.export@lanxess.com

South & Central America
+55.19.3522.5083
atendimento.cliente@lanxess.com

Asia Pacific
+86.21.6109.6666
Orders.apac@lanxess.com

